



RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE

3015

TRADE NAME

Super Chloroprene Sheet

POLYMER:

CR

APPLICATION

Chloroprene

| CHARACTERISTICS | UNITS OF MEASURE | SPECIFICATIONS | VALUES | TOLERANCE |
|--------------------------|-------------------|----------------|--------|-----------|
| HARDNESS (H): | Sh.A3 | ASTM D 2240 | 60 | ± 5 |
| TENSILE STRENGTH (CR) | MPa | ASTM D 412C | 12 | min. |
| ELONGATION AT BREAK (AR) | % | ASTM D 412C | 400 | min. |
| TEAR STRENGTH | N/mm (.) | ASTM D 624B | 35 | min. |
| ABRASION RESISTANCE | mm ³ | DIN 53516 | | |
| SPECIFIC GRAVITY | g/cm ³ | DIN 53479 | 1,42 | ± 0,03 |

| | | | | |
|-----------|------|-------|------------|------|
| AGEING | Δ H | Sh.A3 | | 5 |
| In: Air | Δ CR | % | ASTM D 573 | - 10 |
| For: 72 h | Δ AR | % | | - 20 |
| At: 70 °C | Δ V | % | | |
| AGEING | Δ H | Sh.A3 | | -3 |
| In: Water | Δ CR | % | ASTM D 471 | |
| For: 72 h | Δ AR | % | | |
| At: 50 °C | Δ V | % | | + 3 |

| | | | | | |
|----------------------|----|------------|------|------|-----------|
| WORKING TEMPERATURES | | | | | |
| In Air | °C | ASTM D 573 | min: | - 20 | max: + 90 |
| In Oil | °C | ASTM D 471 | min: | | max: +50 |
| In Water | °C | ASTM D 471 | min: | | max: +90 |

| MAIN CHARACTERISTICS | | | | | |
|----------------------|-------------|----------|-----------|-----------|-------|
| Elasticity | Compression | Abrasion | Flame | Fuels | Ozone |
| GOOD | GOOD | POOR | EXCELLENT | GOOD/POOR | GOOD |

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.