



RUBBER SHEETS

PHYSICAL PROPERTIES AND TECHNICAL INFORMATION

CODE

4444

TRADE NAME

Super EPDM Sheet

POLYMER:

EPDM

APPLICATION

Ethylene-propylene

CHARACTERISTICS	UNITS OF MEASURE	SPECIFICATIONS	VALUES	TOLERANCE
HARDNESS (H):	Sh.A3	ASTM D 2240	60	± 5
TENSILE STRENGTH (CR)	MPa	ASTM D 412C	12	min.
ELONGATION AT BREAK (AR)	%	ASTM D 412C	450	min.
TEAR STRENGTH	N/mm (.)	ASTM D 624B	25	min.
ABRASION RESISTANCE	mm ³	DIN 53516		
SPECIFIC GRAVITY	g/cm ³	DIN 53479	1,10	± 0,03

AGEING	Δ H	Sh.A3	ASTM D 573	6		
In: Air	Δ CR	%		- 10		
For: 72 h	Δ AR	%		- 30		
At: 100 °C	Δ V	%				
AGEING	Δ H	Sh.A3	ASTM D 1149			
In: Ozone	Δ CR	%		OK		
For: 72 h	Δ AR	%				
At: 30 °C- 100 pphm- all. 50	Δ V	%				
AGEING	Δ H	Sh.A3	ASTM D 471	-3		
In: Water	Δ CR	%				
For: 72 h	Δ AR	%				
At: 100 °C	Δ V	%		+ 3		
WORKING TEMPERATURES						
In Air	°C	ASTM D 573	min:	- 40	max:	+ 120
In Oil	°C	ASTM D 471	min:		max:	
In Water	°C	ASTM D 471	min:		max:	+100

MAIN CHARACTERISTICS

Elasticity	Compression	Abrasion	Flame	Fuels	Ozone
GOOD	GOOD	GOOD/POOR	POOR	UNSUITABLE	EXCELLENT

This data sheet has been issued with the greatest care and it is the result of several proofs made in our laboratory, according to specific norms. We don't ensure that the same tests carried out in other laboratories at the same conditions can give the same results.