

TECHNICAL DATA SHEET

PTFE G453

Properties	Unit	Method	Data - Moulded
PHYSICAL - MECHANICAL			
Density	g/cm ³	ASTM D792	2,05 - 2,11
Hardness - Shore D	/	ASTM D2240	≥ 60
Tensile Strength - CD	N/mm ²	ISO 12086 ISO 527	≥ 13
Elongation at break - CD	%	ISO 12086 ISO 527	≥ 70
Compressive strength at 1% deformation - CD	N/mm ²	ASTM D695	≥ 7
Deformation under load at room temperature after 24 hours at 13,7 N/mm ² - CD	%	ASTM D621	≤ 7
Permanent deformation as above after 24 hours of rest at room temperature - CD	%	ASTM D621	≤ 5
TRIBOLOGICAL			
Dynamic coefficient of friction	/	ASTM D1894 ASTM D3702	0,12 - 0,15
Wear factor K	/	ASTM D3702	0,010 - 0,020
THERMAL			
Service Temperature (min - max)	°C	/	- 200 / + 260
Thermal expansion coefficient (linear) 25 - 100°C	10 ⁻⁵ (mm/mm)/ °C	Similar to ASTM D696	10 - 12
ELECTRICAL			
Volume Resistivity	Ω • cm	ASTM D257	10 ³
Surface Resistivity	Ω	ASTM D257	10 ³

CD=Cross Direction

The data we are herewith providing are all based on laboratory testing and are proposed to technical designers as possible and useful advice. Deviations from the values hereabove indicated may occur, but they do not constitute themselves either detriment of quality or reason for rejection.

REV. 05

May 2011