



PRODUCT CAPABILITIES:

- Rod : 10mm - 50mm
- Sheet : 5mm - 50mm

PRODUCT COLORS:

- Black

ADVANTAGES:

- High Mechanical Strength
- Excellent Wear Resistance
- Chemical Resistance

APPLICATIONS INCLUDE:

- Disk Drive Assembly Fixtures
- Semiconductor/Electronic Components
- Telecommunication Hardware
- Automotive Equipment

** MONOCAST® is the registered trademark of

NIPPON POLYPENCO

GENERAL PROPERTIES	ASTM or UL Test	MC 501CD R2 Typical Values	MC 501CD R6 Typical Values	MC 501CD R9 Typical Values
PHYSICAL				
Specific Gravity (g/cm ³)	D972	1.2	1.23	1.19
MECHANICAL				
Tensile Strength (kgf/cm ²)	D638	700	760	897
Tensile Elongation (%)	D638	10	7	12
Flexural Strength (kgf/cm ²)	D790	1,200	1,200	1,346
Flexural Modulus (10 ³ kgf/cm ²)	D790	42	41	42
IZOD Notched Impact (kgf x cm/2.54cm)	D256	9	9	9
Compressive Strength (10 ³ kgf/cm ²)	D695	1	0.95	0.95
Compressive Modulus (10 ³ kgf/cm ²)	D695	43	41	42
Hardness, Rockwell	D785	R 119	R 117	R 119
THERMAL				
Heat Deflection Temp °F (°C)	D648	392 / 200	392 / 200	392 / 200
ELECTRICAL				
Surface Resistivity (ohms/sq)	D257	10 ² - 10 ⁴	10 ⁶ - 10 ⁸	10 ⁸ - 10 ¹⁰

NOTE: The information contained here in is typical values intended for reference only. They should NOT be used as a basis for design specifications or quality control.