

POMALUX[®] CN-SS

Conductive Acetal Copolymer / Conductive Delrin



** POMALUX® is the registered trademark of

WESTLAKE PLASTICS COMPANY

PRODUCT CAPABILITIES:

• Heavy Gauge Sheet :1/4" - 2"

ADVANTAGES:

- \cdot Stainless Steel Filled
- · Non-Sloughing
- · Dimensionally Stable
- Extremely Strong And Stiff
- · Highly Chemical Resistant
- · Easily Machined

PRODUCT COLORS:

Black

APPLICATIONS INCLUDE:

- · Disk Drive Assembly Fixtures
- \cdot Handling Equipment In The Electrical/
- Electronic Or Semiconductor Industry • Telecommunication Hardware
- · Automotive Equipment

GENERAL PROPERTIES	ASTM or UL Test	POMALUX® CN-SS Typical Values
PHYSICAL		
Specific Gravity (g/cm³)	D792	1.5
Water Absorption, 24 hrs (%)	D570	- 0 ⁰ red
MECHANICAL		
Tensile Strength (psi)	D638	8,600
Tensile Elongation at Yield (%)	D638	-
Flexural Strength (psi)	D790	13,000
Flexural Modulus (psi)	D790	400,000
IZOD Notch <mark>ed</mark> Impact (ft-lb/in)	D256	0.7
IZO <mark>D Un-Notched</mark> Impact (ff-Ib/in)	D256	
Hardness, Shore D	D2240	86
THERMAL	Cl Cl Cad Seams	C3 Grand Secting
Coeff. of Thermal Expansion (x 10 ⁻⁵ in./in./°F)	D696	4.9
Heat Deflection Temp (°F / °C) @ 264 psi	D648	225 / 107
Thermal Conductivity (BTU-in/ft ² -hr-°F)	C177	-
Flammability Rating @ .030"	UL-94	-
ELECTRICAL		
Surface Resistivity (ohms/sq)	D257	10 ² - 10 ⁶
Volume Resistivity (ohm-cm) at 7 <mark>3°F, 50% RH</mark>	D257	10 ² - 10 ⁶
Static Decay, 15% RH (seconds)	MIL- <mark>B-81705-</mark> B	- Row and

NOTE: The information contained here in is typical values intended for reference only, They should NOT be used as a basis for design specifications or quality control.